

Product Information

VESTAKEEP® 2000 CF30

Carbon fiber-reinforced (30%) polyether ether ketone

VESTAKEEP 2000 CF30 is a medium-viscosity, carbon fiber-reinforced (30%) polyether ether ketone for injection molding.

The semi-crystalline polymer features superior mechanical, thermal, and chemical resistance. Parts made from VESTAKEEP 2000 CF30 are self-extinguishing.

VESTAKEEP 2000 CF30 can be processed by common injection molding machines for thermoplastics.

We recommend a melt temperature between 380°C and 400°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP 2000 CF30 is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

For information about processing VESTAKEEP 2000 CF30, please follow the general recommendations in our brochure "VESTAKEEP Polyether Ether Ketone."

For further information, please contact us at evonik-hp@evonik.com.

Property	Test method		Unit	VESTAKEEP 2000 CF30	
	international	national			
Density	23°C	ISO 1183	DIN EN ISO 1183	g/cm ³	1.38
Tensile test		ISO 527-1	DIN EN ISO 527-1		
Tensile strength		ISO 527-2	DIN EN ISO 527-2	MPa	240
Strain at break				%	2
Tensile modulus		ISO 527-1	DIN EN ISO 527-1	MPa	23000
		ISO 527-2	DIN EN ISO 527-2		
CHARPY impact strength		ISO 179/1eU	DIN EN ISO 179/1eU		
	23°C			kJ/m ²	45 C ¹⁾
	-30°C			kJ/m ²	45 C ¹⁾
CHARPY notched impact strength		ISO 179/1eA	DIN EN ISO 179/1eA		
	23°C			kJ/m ²	9 C ¹⁾
	-30°C			kJ/m ²	8 C ¹⁾
Temperature of deflection under load		ISO 75-1	DIN EN ISO 75-1		
		ISO 75-2	DIN EN ISO 75-2		
Method A	1.8	MPa		°C	330
Method B	0.45	MPa		°C	340
Vicat softening temperature		ISO 306	DIN EN ISO 306		
Method A	10 N			°C	343
Method B	50 N			°C	340
Linear thermal expansion		ISO 11359	DIN 53752		
	23–55°C			10 ⁻⁴ K ⁻¹	0.1
longitudinal					
Volume resistivity		IEC 60093	DIN IEC 60093	Ohm · cm	10 ⁶
Surface resistance		IEC 60093	DIN IEC 60093	Ohm	10 ⁵
Melting range		ISO 11357			
DSC	2 nd heating			°C	approx. 340
Melt volume-flow rate (MVR)		ISO 1133	DIN EN ISO 1133		
	380°C/5 kg			cm ³ /10 min	10
Flammability acc. UL94		IEC 60695	UL94		
	1.6 mm				V-0
Glow wire test		IEC 60695-2-	DIN EN 60695-2-		
GWIT	2 mm	12/13	12/13	°C	875
GWFI	2 mm			°C	960
Mold shrinkage		determined on 2 mm sheets			
in flow direction		with film gate at rim		%	0.0
in transverse direction		mold temperature 180°C, ISO 294-4		%	0.4

Pigmentation may affect values.

¹⁾ C = Complete break, incl. hinge break H

® = registered trademark

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. Evonik shall not be responsible for consequential, indirect or incidental damages (including loss of profits) of any kind. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.