

# Vydyne® 21LS

## polyamide 66



Vydyne 21LS is a low-viscosity, general-purpose PA66 resin used for extrusion-compounding. Vydyne 21LS enables mixing shear sensitive materials and high-percent filler concentration where distributive mixing is essential to the final product performance.

The compounded product will maintain its high flow and performance needed for the application. Resistance of Vydyne 21LS to heat, oil and wear is typical of PA66 neat resins.

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Abrasion Resistant • Chemical Resistant • Gasoline Resistant • General Purpose	• Good Toughness • High Rigidity • High Strength • Low Viscosity	• Oil Resistant • Solvent Resistant
Uses	• Compounding		
Agency Ratings	• EC 1935/2004 • EU 10/2011	• EU 2023/2006 • FDA 21 CFR 177.1500	
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Compounding		

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Viscosity Number (H <sub>2</sub> SO <sub>4</sub> (Sulphuric Acid))	113 to 120	cm <sup>3</sup> /g	ISO 307
Bulk Density	674	g/l	ASTM D1895
Moisture Content	0.50	%	ASTM D6869
Relative Viscosity <sup>2</sup>	34.5 to 37.5		ASTM D789

Thermal	Nominal Value	Unit	Test Method
Melting Temperature	260	°C	ISO 11357-3

Optical	Nominal Value	Unit	Test Method
Yellowness Index	4.0	YI	ASTM D1925

**Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Formic acid



**North America**  
+1 888 927 2363

**Europe**  
+32 10 608 600

**Asia**  
+86 21 2315 0888

**Disclaimer of Warranty and Liability**

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.