## Vydyne® 21ZLV polyamide 66



Vydyne 21ZLV is a lower-viscosity, general-purpose PA66 resin. It is available in natural and designed for extrusion-compounding applications. Vydyne 21ZLV is the feedstock of choice for highly filled products and reactive-compounding applications.

Vydyne 21ZLV maintains the chemical resistance typical of PA66 to many chemicals, machine and motor oils, solvents and gasoline.

General			
Material Status	<ul> <li>Commercial: Active</li> </ul>		
Availability	Asia Pacific	• Europe	North America
Features	<ul><li>Abrasion Resistant</li><li>Chemical Resistant</li><li>Gasoline Resistant</li><li>General Purpose</li></ul>	<ul><li>Good Toughness</li><li>High Rigidity</li><li>High Strength</li><li>Low Viscosity</li></ul>	<ul><li>Oil Resistant</li><li>Solvent Resistant</li></ul>
Uses	<ul> <li>Compounding</li> </ul>		
Agency Ratings	<ul><li>EC 1935/2004</li><li>EU 10/2011</li></ul>	<ul><li>EU 2023/2006</li><li>FDA 21 CFR 177.1500</li></ul>	<ul><li>NSF STD-51</li><li>NSF STD-61</li></ul>
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>		
Automotive Specifications	• DELPHI M-7964A		
Appearance	<ul> <li>Natural Color</li> </ul>		
Forms	<ul><li>Pellets</li></ul>		
Processing Method	<ul> <li>Compounding</li> </ul>		
Physical		Nominal Value Unit	Test Method
Density		1.14 g/cm <sup>3</sup>	ISO 1183
Viscosity Number (H2SO4 (Sulphuric Acid))		112 to 122 cm <sup>3</sup> /g	ISO 307
Bulk Density		674 g/l	ASTM D1895
Moisture Content		< 0.35 %	ASTM D6869
Relative Viscosity <sup>2</sup>		34.0 to 37.0	ASTM D789
Thermal		Nominal Value Unit	Test Method
Melting Temperature		260 °C	ISO 11357-3
Optical		Nominal Value Unit	Test Method
Yellowness Index		< 15 YI	ASTM D1925
Additional Information		Nominal Value Unit	Test Method
Amino End Groups <sup>3</sup>		50 mmol/kg, min	Internal Method

© 2019 Ascend Performance Materials Operations. The Ascend Performance Materials and Vydyne marks and logos are trademarks or registered trademarks of Ascend Performance Materials Operations.

## Vydyne® 21ZLV polyamide 66



## **Notes**

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Formic acid

<sup>3</sup> STM-00344 (APM internal test protocol)



North America +1 888 927 2363 **Europe** +32 10 608 600

Asia

+86 21 2315 0888

## **Disclaimer of Warranty and Liability**

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.

© 2019 Ascend Performance Materials Operations. The Ascend Performance Materials and Vydyne marks and logos are trademarks or registered trademarks of Ascend Performance Materials Operations.