

Vydyne® 85XFS

polyamide 66/6 copolymer



Vydyne 85XFS is a general-purpose PA66/6 copolymer resin. It is available in natural and is designed for extrusion-compounding applications. This copolymer PA66/6 resin provides a lower melting point and can be used for compounding thermally sensitive additives or fillers. This resin offers a well balanced combination of engineering properties characterized by high

strength, rigidity, good toughness, high melt point, good surface lubricity and abrasion resistance.

Vydyne 85XFS maintains the chemical resistance typical of PA66/6 to many chemicals, machine and motor oils, solvents and gasoline.

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Abrasion Resistant • Chemical Resistant • Copolymer • Gasoline Resistant	• General Purpose • Good Toughness • High Rigidity • High Strength	• Oil Resistant • Solvent Resistant
Uses	• Compounding		
Agency Ratings	• EC 1935/2004	• EU 10/2011	• EU 2023/2006
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Compounding		
Physical		Nominal Value Unit	Test Method
Density		1.14 g/cm ³	ISO 1183
Viscosity Number (H ₂ SO ₄ (Sulphuric Acid))		135 to 146 cm ² /g	ISO 307
Bulk Density		674 g/l	ASTM D1895
Moisture Content		0.50 %	ASTM D6869
Relative Viscosity ²		44.0 to 50.0	ASTM D789
Thermal		Nominal Value Unit	Test Method
Melting Temperature		245 °C	ISO 11357-3
Optical		Nominal Value Unit	Test Method
Yellowness Index		4.0 YI	ASTM D1925

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.

² Formic acid



North America

+1 888 927 2363

Europe

+32 10 608 600

Asia

+86 21 2315 0888

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.