

Vydyne® R860 BK02

polyamide 66



Vydyne R860 BK02 is general-purpose, glass-fiber and mineral-reinforced PA66 resin. Available in black, this product is also lubricated for improved flow and offers superior surface appearance.

Glass fiber and mineral-reinforced Vydyne resins provide higher heat distortion temperature, resistance to creep and better dimensional stability when compared with unreinforced PA66. These products have good chemical resistance to a broad range of chemicals including gasoline, hydraulic fluids and most solvents.

Typical Applications/End Uses:

Vydyne R860 BK02 can be successfully used in a wide range of injection-molding engineering applications. Typical parts include automotive clips, radiator shrouds, fans and mirror brackets; electrical connectors, housings and bobbins; and industrial applications such as gears, bearing shells, covers and housings.

General				
Material Status	• Commercial: Active			
Availability	• Asia Pacific	• Europe	• North America	
Filler / Reinforcement	• Glass Fiber	• Mineral		
Additive	• Lubricant			
Features	• Good Mold Release • High Rigidity	• High Strength • High Tensile Strength	• Lubricated • Outstanding Surface Finish	
Uses	• Automotive Under the Hood • Bearings	• Connectors • Housings		
Agency Ratings	• ASTM D4066 PA114R35	• ASTM D6779 PA084R35		
Automotive Specifications	• BOSCH VDA EMPB • CHRYSLER MS-DB-41 CPN 2554	• FORD ESB-M4D353-A7 • GM GMP.PA66.003	• GM GMP.PA66.042R • HYUNDAI MS211-47 Type C	
UL File Number	• E70062			
Appearance	• Black			
Forms	• Pellets			
Processing Method	• Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.47	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	0.80	--	%	
Flow : 23°C, 2.00 mm	0.25	--	%	
Water Absorption				ISO 62
24 hr, 23°C	0.60	--	%	
Equilibrium, 23°C, 50% RH	2.0	--	%	

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	10000	5900	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	120	90.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.5	2.8	%	ISO 527-2
Flexural Modulus (23°C)	9000	4500	MPa	ISO 178
Flexural Stress (23°C)	190	97.0	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-30°C	3.8	6.0	kJ/m ²	
23°C	4.4	10	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-30°C	43	60	kJ/m ²	
23°C	48	56	kJ/m ²	
Notched Izod Impact Strength				ISO 180
-30°C	4.6	6.5	kJ/m ²	
23°C	5.6	10	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	230	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	215	--	°C	ISO 75-2/A
Melting Temperature	255	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	2.4E-4	--	cm/cm/°C	
Transverse : 23 to 55°C, 2.00 mm	6.9E-4	--	cm/cm/°C	
Injection	Dry Unit			
Drying Temperature	80 °C			
Drying Time	4.0 hr			
Suggested Max Regrind	25 %			
Rear Temperature	280 to 310 °C			
Middle Temperature	280 to 310 °C			
Front Temperature	280 to 310 °C			
Nozzle Temperature	280 to 310 °C			
Processing (Melt) Temp	285 to 305 °C			
Mold Temperature	65 to 95 °C			

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.